

A ScanControl+™ Ready Material:
 Optimized performance when
 used with the Neo®800+ printer.

Somos® PerFORM Reflect™

Stereolithography

In motorsports – as in automotive, rail and aerospace – speed is key. Getting ready for a race, from design to the track you need to be the fastest. Printing your wind tunnel models with Somos® PerFORM Reflect saves more than 30% post treatment. So, you can get your aerodynamic designs onto your vehicle faster – and be more competitive on the track, road, rail or air.

In Formula One, typically a car body is printed at 60% of its normal size for simulation purposes and checked with particle imaging velocimetry (PIV) in critical areas. Somos® PerFORM Reflect is a new and unique stereolithography material developed specifically for 3D printing parts for wind tunnel testing with PIV. With this innovation, Stratasys again sets a standard in enabling faster aerodynamic design optimizations – in motorsports and beyond.

Somos® PerFORM Reflect produces strong, stiff, high-temperature resistant composite parts that are ideal for wind tunnel testing. Extensive tests show that the new **Somos® PerFORM Reflect** reduces post-processing by more than 30% as it eliminates the need for additional PIV coatings. This translates into faster data collection, decreasing overall lead time per design iteration and allowing customers to conduct iterations faster.

Somos® PerFORM Reflect utilizes patented new technology that allows for reducing and even eliminating much of the finishing work required with traditional materials. Based on Stratasys' industry standard **Somos® PerFORM**, **Somos® PerFORM Reflect** demonstrates all the performance attributes that customers rely on such as low viscosity, low settling, fast processing, high stiffness and heat resistance.



Key Benefits

- Ready-to-use material for PIV wind tunnel testing
- Faster image processing, higher accuracy wind tunnel models
- >30% reduction in post-processing time
- Excellent detail resolution
- Improved surface quality, faster part finishing
- Superior high heat properties

Ideal Applications

- Durable, stiff, tough parts
- Wind tunnel testing for aerodynamic design optimization
- High-temperature testing
- Electrical casings
- Automotive housings
- Tooling

Liquid Properties		Optical Properties		
Appearance	Orange	E_c	8.4 mJ/cm ²	[critical exposure]
Viscosity	~1,100 cP @ 30 °C	D_p	4.15 mils	[slope of cue-depth vs ln (E) curve]
Density	~1.61 g/cm ³ @ 25 °C	E_{10}	93.4 mJ/cm ²	[exposure that gives 0.254 mm (.010 in) thickness]



Mechanical Properties		UV Postcure		Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial
D638-14	Tensile Strength	63.3 MPa	9,180	72.4 MPa	10,500 psi
D638-14	Tensile Modulus	10,135 MPa	1,470 ksi	9,653 MPa	1,400 ksi
D638-14	Elongation at Break	0.79%		0.96%	
D638-14	Poisson's Ratio	0.318		0.315	
D790-15e2	Flexural Strength	119 MPa ^a	7,300 psi	130 MPa	18,800 psi
D790-15e2	Flexural Modulus	8,273 MPa	1,200 ksi	7,722 MPa	1,120 ksi
D256A-10e1	Izod Impact (Notched)	16.9 J/m	0.316 ft-lbf/in	20 J/m	0.375 ft-lbf/in
D2240-15	Hardness (Shore D)	92		94	
D570-98	Water Absorption	0.19%		0.14%	

Thermal/Electrical Properties		UV Postcure		Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial
E831-14	C.T.E. -40 – 0 °C (-40 – 32 °F)	26.3 µm/m °C	9,180	25.7 µm/m °C	14.3 µin/in °F
E831-14	C.T.E. 0 – 50 °C (32 – 122 °F)	35.8 µm/m °C	1,470 ks	31.5 µm/m °C	17.5 µin/in °F
E831-14	C.T.E. 50 – 100 °C (122 – 212 °F)	88.3 µm/m °C		50.5 µm/m °C	28.1 µin/in °F
E831-14	C.T.E. 100 – 150 °C (212 – 302 °F)	85.8 µm/m °C		87.4 µm/m °C	48.5 µin/in °F
D150-18	Dielectric Constant 60 Hz	4.22			
D150-18	Dielectric Constant 1 KHz	3.96			
D150-18	Dielectric Constant 1 MHz	3.67		3.65	
D149-09	Dielectric Strength	6.6 kV/mm	675 V/mil	27.5 kV/mm	699 V/mil
E1545-11	Tg via DMA (E'')	70 °C	158 °F	94 °C	201 °F
D648-16	HDT @ 0.46 MPa (66 psi)	94 °C	201 °F	276 °C	529 °F
D150-18	HDT @ 1.81 MPa (264 psi)	76.5 °C	170 °F	122 °C	252 °F

These values may vary and depend on individual machine processing and post-curing practices.



stratasys.com
ISO 9001:2015
Certified

Stratasys Headquarters
5995 Opus Parkway,
Minnetonka, MN 55343
+1 800 801 6491 (US Toll Free)
+1 952 937-3000 (Intl)
+1 952 937-0070 (Fax)

1 Holtzman St.
Science Park
Rehovot, 7670401
Israel
+972 74 745 4000
+972 74 745 5000 (Fax)

MATERIAL DATA SHEET SLA

© 2026 Stratasys Ltd. All rights reserved. Stratasys, Stratasys signet, Somos and PerFORM Reflect are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. MDS_SL_Somos PerFORM Reflect_0726a